



## PATENT ABSTRACTS OF JAPAN

(11) Publication number: **11123547 A**(43) Date of publication of application: **11.05.99**

(51) Int. Cl.

**B23K 9/00**  
**B23K 9/073**  
**B23K 9/095**  
**B23K 31/00**

(21) Application number: **09289739**(22) Date of filing: **22.10.97**(71) Applicant: **CHUO MOTOR WHEEL CO  
LTD HIROSE TECHNOLOGY KK**(72) Inventor: **SUZUKI YUKIMITSU  
MIYAZAKI KATSUNORI  
KAMIYA TARO**

**(54) METHOD FOR JUDGING STABILITY OF  
WELDING AT STATIONAL PART OF ARC  
WELDING AND DEVICE FOR JUDGING  
STABILITY**

## (57) Abstract

**PROBLEM TO BE SOLVED:** To prevent the flowing of welded defective developed caused by the unstability of arc discharging state, in the state welding part of a consumable electrode type gas shielded arc welding.

**SOLUTION:** This device transmits analog signals by detecting the welding current and the welding voltage with detecting means 7, 8. Even analog signal is made to a digital signal by sampling with an A/D converter 9. Based on these digital signals, one or more items among four items of welding current integral value standard deviation during arc in each one period, welding current integral value standard deviation during short circuit in one period, arc/short circuit time ratio standard deviation in each one period and short circuit frequency with a CPU 10 are calculated. When the difference between the calculated value of any item and the corresponding reference value exceeds the permissible range, it is judged that the welding is unstable or defective and the result is displayed.

COPYRIGHT: (C)1999,JPO

